



PHONE: (360) 816-8540
(800) 888-5048
FAX: (360) 816-8541
EMAIL: asphalt@albina.com
INTERNET: www.albina.com

801 Main Street, Vancouver, WA 98660

CQS-1H

PROPERTIES

	MIN	MAX
Viscosity SFS @ 25°C	15	100
Particle charge	Positive	
Sieve %		0.30
Residue by 204°C Distillation, %	57	

TESTS ON RESIDUE FROM DISTILLATION

Penetration @ 25°C	40	90
--------------------	----	----

2/10/2000

Quality Asphalt Products and Service for Over 40 Years