



PHONE: (360) 816-8540
(800) 888-5048
FAX: (360) 816-8541
EMAIL: asphalt@albina.com
INTERNET: www.albina.com

801 Main Street, Vancouver, WA 98660

HFMS-2/HFE-150

PROPERTIES

	MIN	MAX
Viscosity SFS @ 25°C	100	
Storage Stability 1 day		1
Sieve %		0.10**
Residue by 260°C Distillation, %	65	
Oil distillate by volume of emulsion %		7

TESTS ON RESIDUE FROM DISTILLATION

Penetration @ 25°C, dmm	100	300*
Float Test at 60°C, sec	1200	
Ductility @ 25°C, cm.		40

• *Modification of AASHTO M-140

** - AASHTO a 0.30% is acceptable for samples taken at point of use.

•

2/10/2000

Quality Asphalt Products and Service for Over 40 Years