



PHONE: (360) 816-8540
(800) 888-5048
FAX: (360) 816-8541
EMAIL: asphalt@albina.com
INTERNET: www.albina.com

801 Main Street, Vancouver, WA 98660

HFERS-2/HFE-90

PROPERTIES

	MIN	MAX
Viscosity SFS @ 50°C	50	400*
Storage Stability, 1 day		1.0
Demulsibility, 0.02 N CaCL ₂ , 35 ml, %	30*	
Sieve %		0.10**
Residue by 260°C Distillation, %	65	
Oil in distillate by volume, %		3.0

TESTS ON RESIDUE FROM DISTILLATION

Penetration @ 25°C,dmm	90	200*
Float @ 60° C, sec	1200	
Ductility @ 25° C, cm	40	

* Indicates modified AASHTO specification.

** -AASHTO a 0.30% is acceptable for samples taken at point of use.

2/10/2000

Quality Asphalt Products and Service for Over 40 Years