

CRS-LTP

PROPERTIES	MIN	MAX
Viscosity SFS @ 25°C	100	400
Settlement 5 days, % (a)		5
Storage Stability 1 day (b)		1
Particle charge	Positive(c)	
Sieve %		0.10

TESTS ON RESIDUE FROM DISTILLATION

Residue by 177°C Distillation, %	65.0	
Penetration @ 25°C	120	190
Elastic Recovery% @ 25° C	35	
Elastic Recovery% @ 10° C	45	
Solubility in Trichlorethylene, %	97.0	

- (a) The test requirement for settlement may be waived when the emulsified asphalt is used in less that 5 days. or the purchaser may require that the settlement test be run form the time the sample is received until it is used, if the elapsed time is less than 5 days.
- (b) The 24-hour (1 day) storage stability test may be used instead of the 5 day settlement test.
- (c) Must meet a pH requirement of 6.7 maximum (AASHTO T 200 pH of Aqueous Solutions with the Glass Electrode) if the Particle charge test result is inconclusive.