



Tel: (360) 816-8540
Toll Free: (800) 888-5048
Fax: (360) 816-8541
asphalt@albina.com
www.albina.com

801 Main Street
Vancouver WA 98660

HFRS-2/HFE-90

PROPERTIES	MIN	MAX
Viscosity SFS @ 50°C	50	400*
Storage Stability, 1 day		1.0
Demulsibility, 0.02 N CaCL ₂ , 35 ml, %	30*	
Sieve %		0.10**
Residue by 260°C Distillation, %	65	
Oil in distillate by volume, %		7.0
TESTS ON RESIDUE FROM DISTILLATION		
Penetration @ 25°C, dmm	90	200*
Float @ 60°C, sec	1200	
Ductility @ 25°C, cm	40	

*" Indicates modified AASHTO specification.

**"AASHTO a 0.30% is acceptable for samples taken at point of use.

11/06/2018