



Phone 360-816-8540  
 Fax 360-816-8541  
 Email [Asphalt@Albina.com](mailto:Asphalt@Albina.com)  
 Internet [WWW.Albina.Com](http://WWW.Albina.Com)

**PG 58H-22**  
**Product Specification.**  
**AASHTO MS 332**

**TESTS ON ORIGINAL ASPHALT**

**RESULTS**

	Min	Typical	Max
Flash Point (COC), °C	230.00	300.00	
Solubility in TCE, %	99.00	99.56	
Brookfield viscosity @ 135°C, Pa*s		0.415	3.00
G*/sinδ @ kPa	1.00	2.65	
phase Angle @ 58°C		72.40	

**TESTS ON RESIDUE FROM RTFO**

Mass loss, %		0.36	1.00
G*/sinδ @ 58°C, kPa	2.20	4.26	
Phase angle @ 58°C		65.30	
Elastic Recovery @ 2°5C		NA	
MSCR			
Recovery @ .1			
Recovery @ 3.2			
Recovery Diff			
JnR @ .1			
JnR @ 3.2		1.50	2.00
JnR Diff kPa		58.20	75.00%

**TEST ON PAV RESIDUE @100°C**

G*sinδ @ 22°C, kPa		4650.00	6000.00
Creep Stiffness			
S-value @ -12°C, Mpa		220.00	300.00
M-value @ -12.°C	0.300	0.326	

**AASHTO M-332 Specifications**

Please request for current COC

Temp/ Vis curve available apon request.

**Quality Asphalt Products for Over 40 Years!**