



Phone 360-816-8540  
 Fax 360-816-8541  
 Email [Asphalt@Albina.com](mailto:Asphalt@Albina.com)  
 Internet [WWW.Albina.Com](http://WWW.Albina.Com)

# PG 64-10

## Product Specification.

### TESTS ON ORIGINAL ASPHALT

### RESULTS

	Min	Typical	Max
Flash Point (COC), °C	230.00	300.00	
Solubility in TCE, %	99.00	99.56	
Brookfield viscosity @ 135°C, Pa*s		0.42	3.00
G*/sinδ @ kPa	1.00	1.25	
phase Angle @ 64°C		87.60	

### TESTS ON RESIDUE FROM RTFO

Mass loss, %		0.36	1.00
G*/sinδ @ 64°C, kPa	2.20	3.24	
Phase angle @ 64°C		84.60	
Ductility @ 25°C, 5cm/min., cm.	90.00	>100	

### TEST ON PAV RESIDUE@100°C

G*sinδ @ 31°C, kPa		1240.00	5000.00
Creep Stiffness			
S-value @ -0°C, Mpa		47.00	300.00
M-value @ -0.°C	0.300	0.401	

### AASHTO M-320 Specifications

Please request for current COC

Temp/ Vis curve available apon request.

**Quality Asphalt Products for Over 40 Years!**