



Phone 360-816-8540  
 Fax 360-816-8541  
 Email [Asphalt@Albina.com](mailto:Asphalt@Albina.com)  
 Internet [WWW.Albina.Com](http://WWW.Albina.Com)

## PG 64-22

### Product Specification.

#### TESTS ON ORIGINAL ASPHALT

#### RESULTS

	Min	Typical	Max
Flash Point (COC), °C	230.00	300.00	
Solubility in TCE, %	99.00	99.56	
Brookfield viscosity @ 135°C, Pa*s		0.425	3.00
G*/sinδ @ kPa	1.00	1.25	
phase Angle @ 64°C		87.60	

#### TESTS ON RESIDUE FROM RTFO

Mass loss, %		0.36	1.00
G*/sinδ @ 64°C, kPa	2.20	3.24	
Phase angle @ 64°C		84.60	
Ductility @ 25°C, 5cm/min., cm.		NA	

#### TEST ON PAV RESIDUE @100°C

G*sinδ @ 25°C, kPa		3760.00	5000.00
Creep Stiffness			
S-value @ -12°C, Mpa		220.00	300.00
M-value @ -12.°C	0.300	0.332	

#### AASHTO M-320 Specifications

Please request for current COC

Temp/ Vis curve available upon request.

**Quality Asphalt Products for Over 40 Years!**