



Phone 360-816-8540
 Fax 360-816-8541
 Email Asphalt@Albina.com
 Internet WWW.Albina.Com

PG 70-22

Product Specification.

TESTS ON ORIGINAL ASPHALT

	RESULTS		
	Min	Typical	Max
Flash Point (COC), °C	230.00	300.00	
Solubility in TCE, %	99.00	99.56	
Brookfield viscosity @ 135°C, Pa*s		0.686	3.00
G*/sinδ @ kPa	1.00	1.20	
phase Angle @ 70°C		87.58	

TESTS ON RESIDUE FROM RTFO

Mass loss, %		0.32	1.00
G*/sinδ @ 70°C, kPa	2.20	3.23	
Phase angle @ 70°C		83.70	
Ductility @ 25°C, 5cm/min., cm.		NA	

TEST ON PAV RESIDUE @100°C

G* $\sin\delta$ @ 28°C, kPa		3760.00	5000.00
Creep Stiffness			
S-value @ -12°C, Mpa		205.00	300.00
M-value @ -12.°C	0.300	0.332	

AASHTO M-320 Specifications

Please request for current COC

Temp/ Vis curve available upon request.

Quality Asphalt Products for Over 40 Years!