

MC-70

Specifications

These materials shall conform to the specifications set forth in the AASHTO M-82 and ASTM D-2027 Standard Specifications for Highway Construction.

TESTS ON ORIGINAL ASPHALT

| | SPECIFICATION |
|--|----------------------|
| Viscosity Kinematic @ 140°F (60°C), cSt | 70-140 |
| Flash point °C, Tag Cup | 38 min |
| Distillation | |
| @225°C | 0-20 |
| @260°C | 20-60 |
| @315°C | 65-90 |

TESTS ON RESIDUE FROM DISTILLATION

| | |
|---------------------|----------|
| Viscosity @ 60°C, P | 300-1200 |
| Solubility (TCE) | 99.0 min |
| Ductility @ 25°C | 100 |