

MC-800

Specifications

These materials shall conform to the specifications set forth in the AASHTO M-82 and ASTM D-2027 Standard Specifications for Highway Construction.

TESTS ON ORIGINAL ASPHALT

	SPECIFICATION
Viscosity Kinematic @ 140°F (60°C), cSt	800-1600
Flash point °C, Tag Cup	66 min
Distillation	
@225°C	-
@260°C	20-35
@315°C	45-80

TESTS ON RESIDUE FROM DISTILLATION

Viscosity @ 60°C, P	300-1200
Solubility (TCE)	99.0 min
Ductility @ 25°C	100