



Phone 360-816-8540
 Fax 360-816-8541
 Email Asphalt@Albina.com
 Internet WWW.Albina.Com

PG 58-34M

Product Specification.

TESTS ON ORIGINAL ASPHALT

RESULTS

	Min	Typical	Max
Flash Point (COC), °C	230.00	300.00	
Solubility in TCE, %	99.00	99.56	
Brookfield viscosity @ 135°C, Pa*s			3.00
G*/sinδ @ 58°C, kPa	1.00	1.26	
phase Angle @ 58C		70.20	

TESTS ON RESIDUE FROM RTFO

Mass loss, %		0.36	1.00
G*/sinδ @ 58°C, kPa	2.20	3.45	
Phase angle @ 58		66.20	
Ductility @ 25°C, 5cm/min., cm.		NA	
AASTHO T-301 ER at 25C	> 75%	80%	

TEST ON PAV RESIDUE @100°C

G* $\sin\delta$ @ 16°C, kPa		2860.00	5000.00
Creep Stiffness			
S-value @ -24°C, Mpa		240.00	300.00
M-value @ -24°C	0.300	0.312	

See AASHTO M-320 Specifications for test procedures.

Please request for current COC

Temp/ Vis curve available upon request.

Quality Asphalt Products for Over 40 Years!