



Phone 360-816-8540  
 Fax 360-816-8541  
 Email [Asphalt@Albina.com](mailto:Asphalt@Albina.com)  
 Internet [WWW.Albina.Com](http://WWW.Albina.Com)

## PG 58S-28

### Product Specification.

#### TESTS ON ORIGINAL ASPHALT

	RESULTS		
	Min	Typical	Max
Flash Point (COC), °C	230.00	300.00	
Solubility in TCE, %	99.00	99.56	
Brookfield viscosity @ 135°C, Pa*s		0.29	3.00
G*/sinδ @ kPa	1.00	1.26	
phase Angle @ 58°C		86.50	

#### TESTS ON RESIDUE FROM RTFO

Mass loss, %		0.36	1.00
G*/sinδ @ 58°C, kPa	2.20	3.24	
Phase angle @ 58°C		82.60	
Elastic Recovery @ 2°5C		NA	
MSCR			
Recovery @ .1			
Recovery @ 3.2			
Recovery Diff			
JnR @ .1			
JnR @ 3.2		4.00	4.50
JnR Diff kPa		66.00	75.00%

#### TEST ON PAV RESIDUE @100°C

G*sinδ @ 19°C, kPa		4650.00	5000.00
Creep Stiffness			
S-value @ -18°C, Mpa		220.00	300.00
M-value @ -18.°C	0.300	0.326	

#### AASHTO M-332 Specifications

Please request for current COC

Temp/ Vis curve available apon request.

**Quality Asphalt Products for Over 40 Years!**