



Phone 360-816-8540  
 Fax 360-816-8541  
 Email [Asphalt@Albina.com](mailto:Asphalt@Albina.com)  
 Internet [WWW.Albina.Com](http://WWW.Albina.Com)

# PG 64-28ER

## Product Specification.

### TESTS ON ORIGINAL ASPHALT

### RESULTS

	Min	Typical	Max
Flash Point (COC), °C	230.00	300.00	
Solubility in TCE, %	99.00	99.56	
Brookfield viscosity @ 135°C, Pa*s		0.705	3.00
G*/sinδ @ 64°C, kPa	1.00	1.23	
phase Angle @ 64C		73.50	

### TESTS ON RESIDUE FROM RTFO

Mass loss, %		0.36	1.00
G*/sinδ @ 64°C, kPa	2.20	3.45	
Phase angle @ 64		66.20	
Ductility @ 25°C, 5cm/min., cm.		NA	
AASTHO T-301 ER at 25C	> 50%	65%	

### TEST ON PAV RESIDUE @100°C

G* $\sin\delta$ @ 22°C, kPa		3460.00	5000.00
Creep Stiffness			
S-value @ -18°C, Mpa		215.00	300.00
M-value @ -18°C	0.300	0.325	

**See AASHTO M-320 Specifications for test procedures.**

**Please request for current COC**

**Temp/ Vis curve available upon request.**

**Quality Asphalt Products for Over 40 Years!**