



Phone 360-816-8540
 Fax 360-816-8541
 Email Asphalt@Albina.com
 Internet WWW.Albina.Com

PG 64-28M

Product Specification.

TESTS ON ORIGINAL ASPHALT

RESULTS

	Min	Typical	Max
Flash Point (COC), °C	230.00	300.00	
Solubility in TCE, %	99.00	99.56	
Brookfield viscosity @ 135°C, Pa*s		0.715	3.00
G*/sinδ @ 64°C, kPa	1.00	2.35	
phase Angle @ 64C		72.50	

TESTS ON RESIDUE FROM RTFO

Mass loss, %		0.36	1.00
G*/sinδ @ 64°C, kPa	2.20	4.26	
Phase angle @ 64		66.20	
Phase angle @ 2.20		65.00	
AASTHO T-301 ER at 25C	> 75%	81%	

TEST ON PAV RESIDUE @100°C

G* $\sin\delta$ @ 22°C, kPa		3460.00	5000.00
Creep Stiffness			
S-value @ -18°C, Mpa		215.00	300.00
M-value @ -18°C	0.300	0.325	

See AASHTO M-320 Specifications for test procedures.

Please request for current COC

Temp/ Vis curve available upon request.

Quality Asphalt Products for Over 40 Years!