



Phone 360-816-8540
 Fax 360-816-8541
 Email Asphalt@Albina.com
 Internet WWW.Albina.Com

PG 64V-28

Product Specification.

TESTS ON ORIGINAL ASPHALT

	RESULTS		
	Min	Typical	Max
Flash Point (COC), °C	230.00	300.00	
Solubility in TCE, %	99.00	99.56	
Brookfield viscosity @ 135°C, Pa*s		0.715	3.00
G*/sinδ @ kPa @64°C	1.00	4.10	
phase Angle @ 64°C		72.30	

TESTS ON RESIDUE FROM RTFO

Mass loss, %		0.36	1.00
G*/sinδ @ 64°C, kPa	2.20	5.95	
Phase angle @ 64°C		64.20	
Elastic Recovery @ 25°C	60.00%	65.00	
MSCR			
Recovery @ .1			
Recovery @ 3.2	30.00%	35.00	
Recovery Diff			
JnR @ .1			
JnR @ 3.2		0.61	1.00
JnR Diff kPa		58.00	75.00%

TEST ON PAV RESIDUE @100°C

G*sinδ @ 22°C, kPa		3680.00	6000.00
Creep Stiffness			
S-value @ -18°C, Mpa		180.00	300.00
M-value @ -18.°C	0.300	0.326	

AASHTO M-332 Specifications

Please request for current COC

Temp/ Vis curve available apon request.

Quality Asphalt Products for Over 40 Years!