



Phone 360-816-8540
 Fax 360-816-8541
 Email Asphalt@Albina.com
 Internet WWW.Albina.Com

PG 70-28ER

Product Specification.

TESTS ON ORIGINAL ASPHALT

RESULTS

	Min	Typical	Max
Flash Point (COC), °C	230.00	300.00	
Solubility in TCE, %	99.00	99.56	
Brookfield viscosity @ 135°C, Pa*s		0.710	3.00
G*/sinδ @ 70°C, kPa	1.00	1.23	
phase Angle @ 70C		87.80	

TESTS ON RESIDUE FROM RTFO

Mass loss, %		0.36	1.00
G*/sinδ @ 70°C, kPa	2.20	2.49	
Phase angle @ 70		66.20	
Ductility @ 25°C, 5cm/min., cm.		NA	
AASTHO T-301 ER at 25C	> 60%	65%	

TEST ON PAV RESIDUE

G* $\sin\delta$ @ 25°C, kPa		3580.00	5000.00
Creep Stiffness			
S-value @ -18°C, Mpa		207.00	300.00
M-value @ -18°C	0.300	0.337	

AASTHO M-320 Specifications

Please request for current COC

Temp/ Vis curve available upon request.

Quality Asphalt Products for Over 40 Years!