

SC-250

Specifications

These materials shall conform to the specifications set forth in the AASHTO M-82 and ASTM D-2027 Standard Specifications for Highway Construction.

TESTS ON ORIGINAL ASPHALT

	SPECIFICATION
Viscosity Kinematic @ 140°F (60°C), cSt	250-500
Flash point °C, Tag Cup	79 min
Distillation at 360C	
Distillate Volume %	4-20

TESTS ON RESIDUE FROM DISTILLATION

Viscosity @ 60°C, cSt	800-10000
Solubility (TCE)	99.0 min
Ductility @ 25°C	100