

SC-800

Specifications

These materials shall conform to the specifications set forth in the AASHTO M-82 and ASTM D-2027 Standard Specifications for Highway Construction.

TESTS ON ORIGINAL ASPHALT

| | SPECIFICATION |
|--|---------------|
| Viscosity Kinematic @ 140°F (60°C), cSt | 800-1600 |
| Flash point °C, Tag Cup | 79 min |
| Distillation at 360C | |
| Distillate Volume % | 2-12 |

TESTS ON RESIDUE FROM DISTILLATION

| | |
|-----------------------|------------|
| Viscosity @ 60°C, cSt | 2000-16000 |
| Solubility (TCE) | 99.0 min |
| Ductility @ 25°C | 100 |