



Tel: (360) 816-8540  
Toll Free: (800) 888-5048  
Fax: (360) 816-8541  
asphalt@albina.com  
www.albina.com

801 Main Street  
Vancouver WA 98660

## AC-15P

A polymer modified, hot applied, chip seal binder formulated with select binder stock and special polymers to insure lasting adhesion of the chip aggregates to the existing pavement. Can be adjusted within the specification given your climatic region.

**AC-15P allows you to spray it, chip it, roll it and sweep it .....All within hours of placement!!!!**

High ADT's roads are no problem for AC-15P.....Brooming minutes behind the rollers eliminate loose rock in hours, not days, and **reduce exposure of flying rock damage.**

AC-15P is already included in the Maintenance Bids for both the State of Washington and Oregon and numerous projects are completed and performing extremely well.

### AC-15P Specification

Property	TEST	Min.	Max
Original DSR @ 64 °C kPa	AASHTO T-315	1.00	1.90
Kinematic Viscosity @ 275F, cst	AASHTO T201		1200
Penetration@ 25C, 100g, 5sec.,dmm	AASHTO T49	90	150
Elastic Recovery % @ 10 C	ODOT TM429	70	
Cleveland Open Cup (Flash Pt) C	AASHTO T48	260	